

WHAT IS CLAIMED IS

1. A catalyst for use in oxidation or reduction reactions, the catalyst comprising platinum, zinc, and at least one of nickel and iron.
2. The catalyst of claim 1 consisting essentially of platinum, zinc, and at least one of nickel and iron.
3. The catalyst of claim 1 comprising a concentration of platinum that is between about 10 and about 80 atomic percent.
4. The catalyst of claim 1 comprising a concentration of zinc that is between about 2 and about 70 atomic percent.
5. The catalyst of claim 1 comprising a concentration of nickel, iron, or combination thereof that is between about 5 and about 80 atomic percent.
6. The catalyst of claim 1 comprising a concentration of platinum that is between about 10 and about 80 atomic percent, a concentration of zinc that is between about 2 and about 70 atomic percent, and a concentration of nickel, iron, or combination thereof that is between about 5 and about 80 atomic percent.
7. The catalyst of claim 1 comprising a concentration of platinum that is between about 15 and about 60 atomic percent, a concentration of zinc that is between about 5 and about 60 atomic percent, and a concentration of nickel, iron, or combination thereof that is between about 10 and about 70 atomic percent.
8. The catalyst of claim 1 comprising a concentration of platinum that is between about 10 and about 80 atomic percent, a concentration of zinc that is between about 5 and about 60 atomic percent, and a concentration of nickel that is between about 10 and about 70 atomic percent.
9. The catalyst of claim 1 comprising a concentration of platinum that is between about 15 and about 50 atomic percent, a concentration of zinc that is between about 15

and about 50 atomic percent, and a concentration of nickel that is between about 20 and about 60 atomic percent.

10. The catalyst of claim 1 comprising a concentration of platinum that is between about 20 and about 35 atomic percent, a concentration of zinc that is between about 20 and about 40 atomic percent, and a concentration of nickel that is between about 30 and about 55 atomic percent.

11. The catalyst of claim 1 comprising a concentration of platinum that is between about 20 and about 30 atomic percent, a concentration of zinc that is between about 5 and about 15 atomic percent, and a concentration of nickel that is between about 60 and about 70 atomic percent.

12. The catalyst of claim 1 comprising a concentration of platinum that is between about 10 and about 80 atomic percent, a concentration of zinc that is between about 2 and about 70 atomic percent, and a concentration of iron that is between about 5 and about 80 atomic percent.

13. The catalyst of claim 1 comprising a concentration of platinum that is between about 20 and about 60 atomic percent, a concentration of zinc that is between about 5 and about 50 atomic percent, and a concentration of iron that is between about 10 and about 80 atomic percent.

14. The catalyst of claim 1 comprising a concentration of platinum that is between about 35 and about 50 atomic percent, a concentration of zinc that is between about 5 and about 35 atomic percent, and a concentration of iron that is between about 20 and about 60 atomic percent.

15. The catalyst of claim 1 comprising a concentration of platinum that is between about 40 and about 60 atomic percent, a concentration of zinc that is between about 10 and about 30 atomic percent, and a concentration of iron that is between about 25 and about 50 atomic percent.

16. The catalyst of claim 1 comprising a concentration of platinum that is

between about 20 and about 40 atomic percent, a concentration of zinc that is between about 20 and about 50 atomic percent, and a concentration of iron that is between about 25 and about 40 atomic percent.

17. The catalyst as in any one of claims 1-16 wherein the catalyst is an alloy comprising platinum, zinc, and at least one of nickel and iron.

18. A supported electrocatalyst powder for use in electrochemical reactor devices, the supported electrocatalyst powder comprising the catalyst as in any one of claims 1-17 and electrically conductive support particles upon which the catalyst is dispersed.

19. The supported electrocatalyst powder of claim 18 wherein the electrically conductive support particles are selected from the group consisting of inorganic supports and organic supports.

20. The supported electrocatalyst powder of claim 19 wherein the electrically conductive support particles are selected from the group consisting of carbon supports and electrically conductive polymer supports.

21. A fuel cell electrode, the fuel cell electrode comprising electrocatalyst particles and an electrode substrate upon which the electrocatalyst particles are deposited, the electrocatalyst particles comprising the catalyst as in any one of claims 1-17.

22. The fuel cell electrode of claim 21 wherein the electrocatalyst particles comprise electrically conductive support particles upon which the catalyst is dispersed.

23. The fuel cell electrode of claim 22 wherein the electrically conductive support particles are selected from the group consisting of carbon supports and electrically conductive polymer supports.

24. A fuel cell comprising an anode, a cathode, a proton exchange membrane between the anode and the cathode, and the catalyst as in any one of claims 1-17 for

the catalytic oxidation of a hydrogen-containing fuel or the catalytic reduction of oxygen.

25. The fuel cell of claim 24 wherein the fuel consists essentially of hydrogen.

26. The fuel cell of claim 24 wherein the fuel is a hydrocarbon-based fuel.

27. The fuel cell of claim 24 wherein the fuel comprises methanol.

28. The fuel cell of claim 24 wherein the catalyst is on the surface of the proton exchange membrane and in contact with the anode.

29. The fuel cell of claim 24 wherein the catalyst is on the surface of the anode and in contact with the proton exchange membrane.

30. The fuel cell of claim 24 wherein the catalyst is on the surface of the proton exchange membrane and in contact with the cathode.

31. The fuel cell of claim 24 wherein the catalyst is on the surface of the cathode and in contact with the proton exchange membrane.

32. A method for the electrochemical conversion of a hydrogen-containing fuel and oxygen to reaction products and electricity in a fuel cell comprising an anode, a cathode, a proton exchange membrane therebetween, the catalyst as in any one of claims 1-17, and an electrically conductive external circuit connecting the anode and
5 cathode, the method comprising contacting the hydrogen-containing fuel or the oxygen and the catalyst to catalytically oxidize the hydrogen-containing fuel or catalytically reduce the oxygen.

33. The method of claim 32 wherein the hydrogen-containing fuel consists essentially of hydrogen.

34. The method of claim 32 wherein the hydrogen-containing fuel is a hydrocarbon-based fuel selected from the group consisting of saturated hydrocarbons, garbage off-gas, oxygenated hydrocarbons, fossil fuels, and mixtures thereof.

RECEIVED BY
ATTORNEY
JUL 22 2003

35. The method of claim 32 wherein the hydrogen-containing fuel is methanol.

36. An unsupported catalyst layer on a surface of a electrolyte membrane or an electrode, said unsupported catalyst layer comprising platinum, zinc, and at least one of nickel and iron.